

PARKHOUSE ENTERPRISES LTD.

INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS

3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU

Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com

CEMENT TEST RESULTS

Client :- **Dragon Cement 52.5 N**
Our Reference :- **DG52-1**
Sample :- **CEM 1 52.5N**
Sand :- **German**
Date of receipt of sample :- **21-Dec-13**
Date of tests :- **23-Dec-13** to **18-Jan-14**

RESULTS

INITIAL SETTING TIME **160 mins** (BS EN196 PART 3:2005)

COMPRESSIVE STRENGTH :- MORTAR PRISMS (BS EN196 PART 1:2005)


AT 2 DAYS **33.9 MPa** (Mean of 6 results,none discarded)

AT 28 DAYS **65.5 MPa** (Mean of 6 results,none discarded)

CHEMICAL COMPOSITION :- by mass

Loss on ignition **1.04 %** (BS EN196 PART2:2013)

Insoluble Residue **0.29 %** (BS EN196 PART2:2013)

Signed.....
S.Burton A.M.I.C.T **Technical Manager**
J.Burton **Quality Manger**

Date **30-Jan-14**