

# ***PARKHOUSE ENTERPRISES LTD.***

INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS

3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU

Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com

## **CEMENT TEST RESULTS**

Client	:-	Dragon Cement 52.5 R		
Our Reference	:-	DG52-3		
Sample	:-	CEM 1 52.5 R		
Sand	:-	German		
Date of receipt of sample	:-	21-Jan-14		
Date of tests	:-	21-Jan-14	to	18-Feb-14

### RESULTS

INITIAL SETTING TIME	145 mins	(BS EN196 PART 3:2005)
----------------------	----------	------------------------

COMPRESSIVE STRENGTH :- MORTAR PRISMS		(BS EN196 PART 1:2005)
---------------------------------------	--	------------------------

AT 2 DAYS	36.1 MPa	(Mean of 6 results,none discarded)
-----------	----------	------------------------------------

AT 28 DAYS	61.9 MPa	(Mean of 6 results,none discarded)
------------	----------	------------------------------------

CHEMICAL COMPOSITION :- by mass		
---------------------------------	--	--

Loss on ignition	1.21 %	(BS EN196 PART2:2013)
------------------	--------	-----------------------

Insoluble Residue	0.39 %	(BS EN196 PART2:2013)
-------------------	--------	-----------------------

Signed.....  
S. Sykes Senior Technician

Date 18-Feb-14