

# ***PARKHOUSE ENTERPRISES LTD.***

**INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS**

**3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU  
Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com**

## **CEMENT TEST RESULTS**

**Client** :- **Dragon Cement 42.5R**  
**Our Reference** :- **DG42-4**  
**Sample** :- **CEM 1 42.5R**  
**Sand** :- **German**  
**Date of receipt of sample** :- **27-Jan-14**  
**Date of tests** :- **27-Jan-14** to **24-Feb-14**

### **RESULTS**

**INITIAL SETTING TIME**                      **175 mins**                      (BS EN196 PART 3:2005)

**COMPRESSIVE STRENGTH :- MORTAR PRISMS**                      (BS EN196 PART 1:2005)


**AT 2 DAYS**                                      **33.2 MPa**                      (Mean of 6 results,none discarded)

**AT 28 DAYS**                                      **57.6 MPa**                      (Mean of 6 results,none discarded)

**CHEMICAL COMPOSITION :- by mass**

**Loss on ignition**                              **1.77 %**                      (BS EN196 PART2:2013)

**Insoluble Residue**                              **0.59 %**                      (BS EN196 PART2:2013)

**Signed**.....  
**S. Sykes Senior Technician**

**Date**      **24-Feb-14**