

# ***PARKHOUSE ENTERPRISES LTD.***

**INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS**

**3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU**

**Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com**

## **CEMENT TEST RESULTS**

**Client** :- **Dragon Cement 52.5 R**  
**Our Reference** :- **DG52-7**  
**Sample** :- **CEM 1 52.5 R**  
**Sand** :- **German**  
**Date of receipt of sample** :- **18-Feb-14**  
**Date of tests** :- **18-Feb-14** to **18-Mar-14**

### **RESULTS**

**INITIAL SETTING TIME** **135 mins** (BS EN196 PART 3:2005)

**COMPRESSIVE STRENGTH :- MORTAR PRISMS** (BS EN196 PART 1:2005)

**AT 2 DAYS** **36.1 MPa** (Mean of 6 results,none discarded)

**AT 28 DAYS** **61.5 MPa** (Mean of 6 results,none discarded)

**CHEMICAL COMPOSITION :- by mass**

**Loss on ignition** **1.55 %** (BS EN196 PART2:2013)

**Insoluble Residue** **0.47 %** (BS EN196 PART2:2013)

  
Signed.....  
S. Sykes Senior Technician

**Date** **18-Mar-14**