

# **PARKHOUSE ENTERPRISES LTD.**

**INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS**

**3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU**

**Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com**

## **CEMENT TEST RESULTS**

Client	:-	Dragon Cement 42.5R	
Our Reference	:-	DG42-	108
Sample	:-	CEM 1 42.5R	
Sand	:-	German	
Date of receipt of sample	:-	17-Jun-16	
Date of tests	:-	17-Jun-16	to 15-Jul-16

### **RESULTS**

**INITIAL SETTING TIME** **180 mins** (BS EN196 PART 3:2005)

**COMPRESSIVE STRENGTH :- MORTAR PRISMS** (BS EN196 PART 1:2005)

**AT 2 DAYS** **33.6 MPa** (Mean of 6 results, none discarded)

**AT 28 DAYS** **56.6 MPa** (Mean of 6 results, none discarded)

**CHEMICAL COMPOSITION :- by mass**

**Loss on ignition** **2.87 %** (BS EN196 PART2:2013)

**Insoluble Residue** **0.92 %** (BS EN196 PART2:2013)

**Sulphate** **3.38 %** (BS EN196 PART2:2013)

Signed.....  
**S. Sykes Senior Technician**

**Date 18-Jul-16**