

PARKHOUSE ENTERPRISES LTD.

INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS

3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU

Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com

CEMENT TEST RESULTS

| | | | | |
|----------------------------------|-----------|----------------------------|-----------|------------------|
| Client | :- | Dragon Cement 42.5R | | |
| Our Reference | :- | DG42- 11 | | |
| Sample | :- | CEM 1 42.5R | | |
| Sand | :- | German | | |
| Date of receipt of sample | :- | 17-Mar-14 | | |
| Date of tests | :- | 17-Mar-14 | to | 14-Apr-14 |

RESULTS

INITIAL SETTING TIME **205 mins** (BS EN196 PART 3:2005)

COMPRESSIVE STRENGTH :- MORTAR PRISMS (BS EN196 PART 1:2005)

AT 2 DAYS **31.5 MPa** (Mean of 6 results, none discarded)

AT 28 DAYS **54.3 MPa** (Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass

Loss on ignition **2.47 %** (BS EN196 PART2:2013)

Insoluble Residue **0.41 %** (BS EN196 PART2:2013)

Signed.....

S. Sykes Senior Technician

Date **17-Apr-14**