

PARKHOUSE ENTERPRISES LTD.

INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS

3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU

Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com

CEMENT TEST RESULTS

Client	:-	Dragon Cement 52.5 R	
Our Reference	:-	DG52- 11	
Sample	:-	CEM 1 52.5 R	
Sand	:-	German	
Date of receipt of sample	:-	17-Mar-14	
Date of tests	:-	17-Mar-14	to 14-Apr-14

RESULTS

INITIAL SETTING TIME **160 mins** (BS EN196 PART 3:2005)

COMPRESSIVE STRENGTH :- MORTAR PRISMS (BS EN196 PART 1:2005)

AT 2 DAYS **36.6 MPa** (Mean of 6 results, none discarded)

AT 28 DAYS **63.6 MPa** (Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass

Loss on ignition **1.46 %** (BS EN196 PART2:2013)

Insoluble Residue **0.41 %** (BS EN196 PART2:2013)

Signed.....
S. Sykes Senior Technician

Date 17-Apr-14