

# PARKHOUSE ENTERPRISE LTD

INDEPENDENT CONSULTANTS & SPECIALIST MATERIALS SUPPLIERS

3 DUNSTAN HILL, KIRTON LINDSEY, GAINSBOROUGH, LINCOLNSHIRE DN21 4FG  
PHONE: 01652 656931/01652648270 EMAIL: PARKHOUSEENT@AOL.COM

## CEMENT TEST RESULTS

Client	:-	Dragon Cement 42.5R
Our Reference	:-	DG42- 130
Sample	:-	CEM 1 42.5R
Sand	:-	German
Date of receipt of sample	:-	21-Dec-16
Date of tests	:-	21-Dec-16 to 18-Jan-17

### RESULTS

**INITIAL SETTING TIME** 140 mins (BS EN196 PART 3:2005)

**COMPRESSIVE STRENGTH :- MORTAR PRISMS** (BS EN196 PART 1:2005)

**AT 2 DAYS** 26.0 MPa (Mean of 6 results, none discarded)

**AT 28 DAYS** 52.9 MPa (Mean of 6 results, none discarded)

**CHEMICAL COMPOSITION :- by mass**

**Loss on ignition** 2.90 % (BS EN196 PART2:2013)

**Insoluble Residue** 0.59 % (BS EN196 PART2:2013)

**Sulphate** 3.04 % (BS EN196 PART2:2013)

*S.Sykes*

Signed.....  
S. Sykes Senior Technician

Date 18-Jan-17