

PARKHOUSE ENTERPRISE LTD

INDEPENDENT CONSULTANTS & SPECIALIST MATERIALS SUPPLIERS

3 DUNSTAN HILL, KIRTON LINDSEY, GAINSBOROUGH, LINCOLNSHIRE DN21 4FG
PHONE: 01652 656931/01652648270 EMAIL: PARKHOUSEENT@AOL.COM

CEMENT TEST RESULTS

Client :- Dragon Cement 52.5 R
Our Reference :- DG52- 148
Sample :- CEM 1 52.5 R
Sand :- German
Date of receipt of sample :- 27-Apr-17
Date of tests :- 27-Apr-17 to 25-May-17

RESULTS

INITIAL SETTING TIME 180 mins (BS EN196 PART 3:2005)

COMPRESSIVE STRENGTH :- MORTAR PRISMS (BS EN196 PART 1:2005)

AT 2 DAYS 42.5 MPa (Mean of 6 results, none discarded)

AT 28 DAYS 65.4 MPa (Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass

Loss on ignition 1.86 % (BS EN196 PART2:2013)

Insoluble Residue 0.40 % (BS EN196 PART2:2013)

Sulphate 3.36 % (BS EN196 PART2:2013)

End of Report

S.Sykes

Signed.....

S. Sykes: Senior Technician

Date 25-May-17