

PARKHOUSE ENTERPRISE LTD
INDEPENDENT CONSULTANTS & SPECIALIST MATERIALS SUPPLIERS

3 DUNSTAN HILL, KIRTON LINDSEY, GAINSBOROUGH, LINCOLNSHIRE DN21 4FG
PHONE: 01652 656931/01652648270 EMAIL: PARKHOUSEENT@AOL.COM

CEMENT TEST RESULTS

Client	: -	Dragon Cement 42.5R
Our Reference	: -	DG42- 158
Sample	: -	CEM 1 42.5R
Sand	: -	German
Date of receipt of sample	: -	31-Jul-17
Date of tests	: -	31-Jul-17 to 28-Aug-17

RESULTS

INITIAL SETTING TIME **180 mins** (BS EN196 PART 3:2005)

COMPRESSIVE STRENGTH :- MORTAR PRISMS (BS EN196 PART 1:2005)

AT 2 DAYS **31.4 MPa** (Mean of 6 results, none discarded)

AT 28 DAYS **54.1 MPa** (Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass

Loss on ignition **3.37 %** (BS EN196 PART2:2013)

Insoluble Residue **0.47 %** (BS EN196 PART2:2013)

Sulphate **3.44 %** (BS EN196 PART2:2013)

S.Sykes
Signed.....
S. Sykes Senior Technician

Date 28-Aug-17