

PARKHOUSE ENTERPRISES LTD.

INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS

3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU

Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com

CEMENT TEST RESULTS

Client	:-	Dragon Cement 52.5 R	
Our Reference	:-	DG52- 20	
Sample	:-	CEM 1 52.5 R	
Sand	:-	German	
Date of receipt of sample	:-	27-May-14	
Date of tests	:-	27-May-14	to 24-Jun-14

RESULTS

INITIAL SETTING TIME	145 mins	(BS EN196 PART 3:2005)
-----------------------------	-----------------	-------------------------------

COMPRESSIVE STRENGTH :- MORTAR PRISMS **(BS EN196 PART 1:2005)**

AT 2 DAYS	37.9 MPa	(Mean of 6 results,none discarded)
------------------	-----------------	---

AT 28 DAYS	62.4 MPa	(Mean of 6 results,none discarded)
-------------------	-----------------	---

CHEMICAL COMPOSITION :- by mass

Loss on ignition	1.84 %	(BS EN196 PART2:2013)
-------------------------	---------------	------------------------------

Insoluble Residue	0.55 %	(BS EN196 PART2:2013)
--------------------------	---------------	------------------------------

Sulphate	3.40 %	(BS EN196 PART2:2013)
-----------------	---------------	------------------------------

Signed.....

S. Sykes Senior Technician

Date 25-Jun-14