

PARKHOUSE ENTERPRISES LTD.

INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS

3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU

Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com

CEMENT TEST RESULTS

Client :- **Dragon Cement 52.5 R**
Our Reference :- **DG52- 27**
Sample :- **CEM 1 52.5 R**
Sand :- **German**
Date of receipt of sample :- **11-Jul-14**
Date of tests :- **11-Jul-14 to 8-Aug-14**

RESULTS

INITIAL SETTING TIME **160 mins** (BS EN196 PART 3:2005)

COMPRESSIVE STRENGTH :- MORTAR PRISMS (BS EN196 PART 1:2005)

AT 2 DAYS **39.4 MPa** (Mean of 6 results,none discarded)

AT 28 DAYS **60.1 MPa** (Mean of 6 results,none discarded)

CHEMICAL COMPOSITION :- by mass

Loss on ignition **1.5 %** (BS EN196 PART2:2013)

Insoluble Residue **0.47 %** (BS EN196 PART2:2013)

Sulphate **3.27 %** (BS EN196 PART2:2013)

Signed.....

S. Sykes Senior Technician

Date 12-Aug-14