

PARKHOUSE ENTERPRISES LTD.

INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS

3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU

Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com

CEMENT TEST RESULTS

Client :- **Dragon Cement 52.5 R**
Our Reference :- **DG52- 31**
Sample :- **CEM 1 52.5 R**
Sand :- **German**
Date of receipt of sample :- **19-Aug-14**
Date of tests :- **19-Aug-14 to 16-Sep-14**

RESULTS

INITIAL SETTING TIME **180 mins** (BS EN196 PART 3:2005)

COMPRESSIVE STRENGTH :- MORTAR PRISMS (BS EN196 PART 1:2005)

AT 2 DAYS **35.4 MPa** (Mean of 6 results, none discarded)

AT 28 DAYS **61.2 MPa** (Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass

Loss on ignition **1.68 %** (BS EN196 PART2:2013)

Insoluble Residue **0.50 %** (BS EN196 PART2:2013)

Sulphate **3.33 %** (BS EN196 PART2:2013)

Signed.....
S. Sykes Senior Technician

Date 17-Sep-14