

PARKHOUSE ENTERPRISES LTD.

INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS

3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU

Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com

CEMENT TEST RESULTS

Client	:-	Dragon Cement 42.5R	
Our Reference	:-	DG42- 37	
Sample	:-	CEM 1 42.5R	
Sand	:-	German	
Date of receipt of sample	:-	23-Sep-14	
Date of tests	:-	23-Sep-14	to 21-Oct-14

RESULTS

INITIAL SETTING TIME	155 mins	(BS EN196 PART 3:2005)
-----------------------------	-----------------	-------------------------------

COMPRESSIVE STRENGTH :- MORTAR PRISMS **(BS EN196 PART 1:2005)**

AT 2 DAYS	29.1 MPa	(Mean of 6 results,none discarded)
------------------	-----------------	---

AT 28 DAYS	54.4 MPa	(Mean of 6 results,none discarded)
-------------------	-----------------	---

CHEMICAL COMPOSITION :- by mass

Loss on ignition	2.97 %	(BS EN196 PART2:2013)
-------------------------	---------------	------------------------------

Insoluble Residue	0.49 %	(BS EN196 PART2:2013)
--------------------------	---------------	------------------------------

Sulphate	3.27 %	(BS EN196 PART2:2013)
-----------------	---------------	------------------------------

Signed.....

S. Sykes Senior Technician

Date 21-Oct-14