

# **PARKHOUSE ENTERPRISES LTD.**

**INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS**

**3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU**

**Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com**

## **CEMENT TEST RESULTS**

**Client** :- **Dragon Cement 52.5 R**  
**Our Reference** :- **DG52- 43**  
**Sample** :- **CEM 1 52.5 R**  
**Sand** :- **German**  
**Date of receipt of sample** :- **1-Dec-14**  
**Date of tests** :- **1-Dec-14 to 29-Dec-14**

### **RESULTS**

**INITIAL SETTING TIME** **185 mins** (BS EN196 PART 3:2005)

**COMPRESSIVE STRENGTH :- MORTAR PRISMS** (BS EN196 PART 1:2005)

**AT 2 DAYS** **39.9 MPa** (Mean of 6 results, none discarded)

**AT 28 DAYS** **66.4 MPa** (Mean of 6 results, none discarded)

**CHEMICAL COMPOSITION :- by mass**

**Loss on ignition** **1.71 %** (BS EN196 PART2:2013)

**Insoluble Residue** **0.61 %** (BS EN196 PART2:2013)

**Sulphate** **3.39 %** (BS EN196 PART2:2013)

Signed.....

**S. Sykes Senior Technician**

**Date 3-Jan-15**