

PARKHOUSE ENTERPRISES LTD.

INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS

3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU

Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com

CEMENT TEST RESULTS

Client	:-	Dragon Cement 52.5 R
Our Reference	:-	DG52- 46
Sample	:-	CEM 1 52.5 R
Sand	:-	German
Date of receipt of sample	:-	16-Dec-14
Date of tests	:-	16-Dec-14 to 13-Jan-15

RESULTS

INITIAL SETTING TIME **175 mins** (BS EN196 PART 3:2005)

COMPRESSIVE STRENGTH :- MORTAR PRISMS (BS EN196 PART 1:2005)

AT 2 DAYS **41.9 MPa** (Mean of 6 results, none discarded)

AT 28 DAYS **66.1 MPa** (Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass

Loss on ignition **2.16 %** (BS EN196 PART2:2013)

Insoluble Residue **0.98 %** (BS EN196 PART2:2013)

Sulphate **3.54 %** (BS EN196 PART2:2013)

Signed.....

S. Sykes Senior Technician

Date **14-Jan-15**