

PARKHOUSE ENTERPRISES LTD.

INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS

3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU

Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com

CEMENT TEST RESULTS

Client	:-	Dragon Cement 52.5 R	
Our Reference	:-	DG52- 50	
Sample	:-	CEM 1 52.5 R	
Sand	:-	German	
Date of receipt of sample	:-	10-Feb-15	
Date of tests	:-	10-Feb-15	to 10-Mar-15

RESULTS

INITIAL SETTING TIME **185 mins** (BS EN196 PART 3:2005)

COMPRESSIVE STRENGTH :- MORTAR PRISMS (BS EN196 PART 1:2005)

AT 2 DAYS **45.0 MPa** (Mean of 6 results, none discarded)

AT 28 DAYS **69.0 MPa** (Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass

Loss on ignition **2.04 %** (BS EN196 PART2:2013)

Insoluble Residue **0.45 %** (BS EN196 PART2:2013)

Sulphate **3.47 %** (BS EN196 PART2:2013)

Signed.....

S. Sykes Senior Technician

Date 10-Mar-15