

# ***PARKHOUSE ENTERPRISES LTD.***

**INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS**

**3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU**

**Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com**

## **CEMENT TEST RESULTS**

**Client :- Dragon Cement 42.5R**  
**Our Reference :- DG42- 54**  
**Sample :- CEM 1 42.5R**  
**Sand :- German**  
**Date of receipt of sample :- 18-Mar-15**  
**Date of tests :- 18-Mar-15 to 15-Apr-15**

### **RESULTS**

**INITIAL SETTING TIME 190 mins (BS EN196 PART 3:2005)**

**COMPRESSIVE STRENGTH :- MORTAR PRISMS (BS EN196 PART 1:2005)**

**AT 2 DAYS 37.3 MPa (Mean of 6 results,none discarded)**

**AT 28 DAYS 57.2 MPa (Mean of 6 results,none discarded)**

**CHEMICAL COMPOSITION :- by mass**

**Loss on ignition 2.88 % (BS EN196 PART2:2013)**

**Insoluble Residue 0.46 % (BS EN196 PART2:2013)**

**Sulphate 3.06 % (BS EN196 PART2:2013)**

**Signed.....**  
**S. Sykes Senior Technician**

**Date 15-Apr-15**