

# PARKHOUSE ENTERPRISES LTD.

INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS

3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU

Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com

## CEMENT TEST RESULTS

Client :- Dragon Cement 52.5 R  
Our Reference :- DG52- 54  
Sample :- CEM 1 52.5 R  
Sand :- German  
Date of receipt of sample :- 18-Mar-15  
Date of tests :- 18-Mar-15 to 15-Apr-15

### RESULTS

INITIAL SETTING TIME 205 mins (BS EN196 PART 3:2005)

COMPRESSIVE STRENGTH :- MORTAR PRISMS (BS EN196 PART 1:2005)

AT 2 DAYS 38.0 MPa (Mean of 6 results, none discarded)

AT 28 DAYS 67.2 MPa (Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass

Loss on ignition 1.84 % (BS EN196 PART2:2013)

Insoluble Residue 0.81 % (BS EN196 PART2:2013)

Sulphate 3.19 % (BS EN196 PART2:2013)

Signed.....  
S. Sykes Senior Technician

Date 15-Apr-15