

# **PARKHOUSE ENTERPRISES LTD.**

INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS

3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU

Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com

## **CEMENT TEST RESULTS**

Client :- Dragon Cement 42.5R  
Our Reference :- DG42- 65  
Sample :- CEM 1 42.5R  
Sand :- German  
Date of receipt of sample :- 15-Jun-15  
Date of tests :- 15-Jun-15 to 13-Jul-15

### **RESULTS**

**INITIAL SETTING TIME** 180 mins (BS EN196 PART 3:2005)

**COMPRESSIVE STRENGTH :- MORTAR PRISMS** (BS EN196 PART 1:2005)

**AT 2 DAYS** 31.1 MPa (Mean of 6 results, none discarded)

**AT 28 DAYS** 58.2 MPa (Mean of 6 results, none discarded)

**CHEMICAL COMPOSITION :- by mass**

**Loss on ignition** 2.42 % (BS EN196 PART2:2013)

**Insoluble Residue** 0.56 % (BS EN196 PART2:2013)

**Sulphate** 3.17 % (BS EN196 PART2:2013)

Signed.....  
S. Sykes Senior Technician

Date 13-Jul-15