

PARKHOUSE ENTERPRISES LTD.

INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS

3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU

Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com

CEMENT TEST RESULTS

Client	:-	Dragon Cement 42.5R	
Our Reference	:-	DG42- 67	
Sample	:-	CEM 1 42.5R	
Sand	:-	German	
Date of receipt of sample	:-	3-Jul-15	
Date of tests	:-	3-Jul-15	to 31-Jul-15

RESULTS

INITIAL SETTING TIME **190 mins** (BS EN196 PART 3:2005)

COMPRESSIVE STRENGTH :- MORTAR PRISMS (BS EN196 PART 1:2005)

AT 2 DAYS **33.7 MPa** (Mean of 6 results, none discarded)


AT 28 DAYS **56.0 MPa** (Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass

Loss on ignition **2.70 %** (BS EN196 PART2:2013)

Insoluble Residue **0.46 %** (BS EN196 PART2:2013)

Sulphate **2.86 %** (BS EN196 PART2:2013)

Signed.....

S. Sykes Senior Technician

Date 3-Aug-15