

# ***PARKHOUSE ENTERPRISES LTD.***

**INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS**

**3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU**

**Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com**

## **CEMENT TEST RESULTS**

**Client** :- **Dragon Cement 42.5R**  
**Our Reference** :- **DG42- 76**  
**Sample** :- **CEM 1 42.5R**  
**Sand** :- **German**  
**Date of receipt of sample** :- **15-Sep-15**  
**Date of tests** :- **15-Sep-15 to 13-Oct-15**

### **RESULTS**

**INITIAL SETTING TIME** **190 mins** (BS EN196 PART 3:2005)

**COMPRESSIVE STRENGTH :- MORTAR PRISMS** (BS EN196 PART 1:2005)

**AT 2 DAYS** **33.4 MPa** (Mean of 6 results, none discarded)


**AT 28 DAYS** **55.8 MPa** (Mean of 6 results, none discarded)

**CHEMICAL COMPOSITION :- by mass**

**Loss on ignition** **2.62 %** (BS EN196 PART2:2013)

**Insoluble Residue** **0.63 %** (BS EN196 PART2:2013)

**Sulphate** **3.43 %** (BS EN196 PART2:2013)

Signed.....  
  
S. Sykes Senior Technician

**Date** **14-Oct-15**