

PARKHOUSE ENTERPRISES LTD.

INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS

3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU

Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com

CEMENT TEST RESULTS

Client :- Dragon Cement 42.5R
Our Reference :- DG42- 86
Sample :- CEM 1 42.5R
Sand :- German
Date of receipt of sample :- 1-Dec-15
Date of tests :- 1-Dec-15 to 29-Dec-15

RESULTS

INITIAL SETTING TIME 175 mins (BS EN196 PART 3:2005)

COMPRESSIVE STRENGTH :- MORTAR PRISMS (BS EN196 PART 1:2005)

AT 2 DAYS 33.0 MPa (Mean of 6 results, none discarded)

AT 28 DAYS 55.4 MPa (Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass

Loss on ignition 2.55 % (BS EN196 PART2:2013)

Insoluble Residue 0.55 % (BS EN196 PART2:2013)

Sulphate 3.23 % (BS EN196 PART2:2013)

Signed.....


**S. Sykes Senior Technician
AffICT**

Date 6-Jan-16