

PARKHOUSE ENTERPRISES LTD.

INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS

3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU

Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com

CEMENT TEST RESULTS

Client :- Dragon Cement 52.5 R
Our Reference :- DG52- 92
Sample :- CEM 1 52.5 R
Sand :- German
Date of receipt of sample :- 1-Feb-16
Date of tests :- 1-Feb-16 to 29-Feb-16

RESULTS

INITIAL SETTING TIME 200 mins (BS EN196 PART 3:2005)

COMPRESSIVE STRENGTH :- MORTAR PRISMS (BS EN196 PART 1:2005)

AT 2 DAYS 34.5 MPa (Mean of 6 results, none discarded)

AT 28 DAYS 61.6 MPa (Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass

Loss on ignition 2.83 % (BS EN196 PART2:2013)

Insoluble Residue 0.92 % (BS EN196 PART2:2013)

Sulphate 3.43 % (BS EN196 PART2:2013)

End of Report

Signed.....

S. Sykes: Senior Technician

Date 11-Apr-16

Page 1 of 1