

PARKHOUSE ENTERPRISES LTD.

INDEPENDENT CONSULTANTS & SPECIALIST MATERIAL SUPPLIERS

3 Dunstan Hill, Kirton in Lindsey, Gainsborough, North Lincolnshire DN21 4DU

Telephone (01652) 648270 : E-mail ParkhouseEnt@aol.com

CEMENT TEST RESULTS

Client	:-	Dragon Cement 42.5R	
Our Reference	:-	DG42- 98	
Sample	:-	CEM 1 42.5R	
Sand	:-	German	
Date of receipt of sample	:-	11-Apr-16	
Date of tests	:-	11-Apr-16	to 09-May-16

RESULTS

INITIAL SETTING TIME	215 mins	(BS EN196 PART 3:2005)
-----------------------------	-----------------	-------------------------------

COMPRESSIVE STRENGTH :- MORTAR PRISMS		(BS EN196 PART 1:2005)
--	--	-------------------------------

AT 2 DAYS	31.2 MPa	(Mean of 6 results,none discarded)
------------------	-----------------	---

AT 28 DAYS	54.9 MPa	(Mean of 6 results,none discarded)
-------------------	-----------------	---

CHEMICAL COMPOSITION :- by mass		
--	--	--

Loss on ignition	2.65 %	(BS EN196 PART2:2013)
-------------------------	---------------	------------------------------

Insoluble Residue	0.49 %	(BS EN196 PART2:2013)
--------------------------	---------------	------------------------------

Sulphate	3.32 %	(BS EN196 PART2:2013)
-----------------	---------------	------------------------------

Signed.....

S. Sykes Senior Technician

Date **07-Jun-16**