

PARKHOUSE ENTERPRISE LTD

INDEPENDENT CONSULTANTS & SPECIALIST MATERIALS SUPPLIERS

3 DUNSTAN HILL, KIRTON LINDSEY, GAINSBOROUGH, LINCOLNSHIRE DN21 4FG
PHONE: 01652 656931/01652648270 EMAIL: PARKHOUSEENT@AOL.COM

CEMENT TEST RESULTS

Client :- **Dragon Cement 42.5R**
Our Reference :- **DG42- 172**
Sample :- **CEM 1 42.5R**
Sand :- **German**
Date of receipt of sample :- **23-Nov-17**
Date of tests :- **23-Nov-17 to 21-Dec-17**

RESULTS

INITIAL SETTING TIME **141 mins** (BS EN196 PART 3:2005)

COMPRESSIVE STRENGTH :- MORTAR PRISMS (BS EN196 PART 1:2005)

AT 2 DAYS **32.3 MPa** (Mean of 6 results,none discarded)

AT 28 DAYS **51.8 MPa** (Mean of 6 results,none discarded)

CHEMICAL COMPOSITION :- by mass

Loss on ignition **2.86 %** (BS EN196 PART2:2013)

Insoluble Residue **0.50 %** (BS EN196 PART2:2013)

Sulphate **3.08 %** (BS EN196 PART2:2013)

S.Sykes

Signed.....

Date **21-Dec-17**

S. Sykes Senior Technician