

# PARKHOUSE ENTERPRISE LTD

INDEPENDENT CONSULTANTS & SPECIALIST MATERIALS SUPPLIERS

3 DUNSTAN HILL, KIRTON LINDSEY, GAINSBOROUGH, LINCOLNSHIRE DN21 4FG  
PHONE: 01652 656931/01652648270 EMAIL: PARKHOUSEENT@AOL.COM

## CEMENT TEST RESULTS

Client	:-	Dragon Cement 42.5R	
Our Reference	:-	DG42-	187
Sample	:-	CEM 1 42.5R	
Sand	:-	German	
Date of receipt of sample	:-	06-Apr-18	
Date of tests	:-	09-Apr-18	to 07-May-18

### RESULTS

**INITIAL SETTING TIME** 155 mins (BS EN196 PART 3:2005)

**COMPRESSIVE STRENGTH :- MORTAR PRISMS** (BS EN196 PART 1:2005)

**AT 2 DAYS** 30.8 MPa (Mean of 6 results, none discarded)

**AT 28 DAYS** 53.6 MPa (Mean of 6 results, none discarded)

**CHEMICAL COMPOSITION :- by mass**

**Loss on ignition** 2.80 % (BS EN196 PART2:2013)

**Insoluble Residue** 0.38 % (BS EN196 PART2:2013)

**Sulphate** 3.32 % (BS EN196 PART2:2013)

Signed.....

S. Sykes Senior Technician

Date 07-May-18