

# PARKHOUSE ENTERPRISE LTD

INDEPENDENT CONSULTANTS & SPECIALIST MATERIALS SUPPLIERS

3 DUNSTAN HILL, KIRTON LINDSEY, GAINSBOROUGH, LINCOLNSHIRE DN21 4FG  
PHONE: 01652 656931/01652648270 EMAIL: PARKHOUSEENT@AOL.COM

## CEMENT TEST RESULTS

Client	:-	Dragon Cement 52.5 R	
Our Reference	:-	DG52-	178
Sample	:-	CEM 1 52.5 R	
Sand	:-	German	
Date of receipt of sample	:-	15-Jan-18	
Date of tests	:-	15-Jan-18	to 12-Feb-18

### RESULTS

INITIAL SETTING TIME	157 mins	(BS EN196 PART 3:2005)
----------------------	----------	------------------------

COMPRESSIVE STRENGTH :- MORTAR PRISMS		(BS EN196 PART 1:200)
---------------------------------------	--	-----------------------

AT 2 DAYS	35.1 MPa	(Mean of 6 results, none discarded)
-----------	----------	-------------------------------------

AT 28 DAYS	63.5 MPa	(Mean of 6 results, none discarded)
------------	----------	-------------------------------------

CHEMICAL COMPOSITION :- by mass

Loss on ignition	3.14 %	(BS EN196 PART2:2013)
------------------	--------	-----------------------

Insoluble Residue	0.48 %	(BS EN196 PART2:2013)
-------------------	--------	-----------------------

Sulphate	3.14 %	(BS EN196 PART2:2013)
----------	--------	-----------------------

End of Report

*S.Sykes*

Signed.....

Date 12-Feb-18

S. Sykes: Senior Technician