



CEMENTOS ALFA, S.A.

PLANT: MATAPORQUERA

ER Certificate: ER-0572/1998



TECHNICAL CHARACTERISTICS CERTIFICATE

Cement

CEM I 42,5 R

Period

February, 2016

**N: 015/001358
CE: 0099/CPR/A33/0154**

TESTS	Results Average Value	Standard Spec. EN/UNE
Chemical Characteristics		
Loss on Ignition %	2,6	< 5,0
Insoluble Residue %	0,6	< 5,0
Sulphates (SO ₃) %	3,3	< 4,0
Chlorides %	0,01	< 0,10
Physical and Mechanical Characteristics		
Normal Consistency Water %	30,0	
Initial Setting Time min	171	> 60
Final Setting Time min	228	< 720
Soundness Le Chatelier mm	0,3	< 10
Specific Surface (Blaine) cm ² /g	3716	
Compressive Strength at 2 days MPa		
• Monthly average	34,8	> 20,0
• Cumulative average (03/2015 - 02/2016)	34,5	> 20,0
• Cumulative Std. Dev. (03/2015 - 02/2016)	1,6	
Compressive Strength at 28 days MPa		
• Monthly average	57,9	42,5 - 62,5
• Cumulative average (03/2015 - 02/2016)	57,7	42,5 - 62,5
• Cumulative Std. Dev. (03/2015 - 02/2016)	1,9	

This document doesn't imply that any amount of cement has been supplied by the Company

Barrio la Estación, s/n.
39410 Mataporquera (Cantabria)
Tel. 942 770 058
Fax 942 770 243
info@alfainforma.com
www.valderrivas.es

Chief of Quality Control

