



**CEMENTOS ALFA, S.A.**

**PLANT: MATAPORQUERA**

ER Certificate: ER-0572/1998



**TECHNICAL CHARACTERISTICS CERTIFICATE**

**Cement**

**Period**

**CEM I 52.5 R MA**

**July, 2017**

**CE: 0099/CPR/A33/0831**

TESTS	Results Average Value	Standard Spec. EN/UNE
<b>Chemical Characteristics</b>		
Loss on Ignition %	2,5	< 5,0
Insoluble Residue %	0,4	< 5,0
Sulphates (SO <sub>3</sub> ) %	3,3	< 4,0
Chlorides %	0,01	< 0,10
<b>Physical and Mechanical Characteristics</b>		
Normal Consistency Water %	30,3	
Initial Setting Time min	162	> 45
Final Setting Time min	221	< 720
Soundness Le Chatelier mm	0,2	< 10
Specific Surface (Blaine) cm <sup>2</sup> /g	4922	
Compressive Strength at 2 days MPa		
• Monthly average	40,7	> 30,0
• Cumulative average (08/2016 - 07/2017)	39,4	> 30,0
• Cumulative Std. Dev. (08/2016 - 07/2017)	2,7	
Compressive Strength at 28 days MPa		
• Monthly average	67,1	> 52,5
• Cumulative average (08/2016 - 07/2017)	66,2	> 52,5
• Cumulative Std. Dev. (08/2016 - 07/2017)	2,9	
<b>Additional Characteristics</b>		
C3A * (%)	4,7	
Alkali Equivalent (%)	0,66	< 0,75

\* Corresponding to clinker composition

This document doesn't imply that any amount of cement has been supplied by the Company

Barrio la Estación, s/n.  
39410 Mataporquera (Cantabria)  
Tel. 942 770 058  
Fax 942 770 243  
info@alfainforma.com  
www.valderrivas.es

Chief of Quality Control

