



CEMENTOS ALFA, S.A,

Plant: MATAPORQUERA

ER Certificate: ER-0572/1998



QUALITY ANALYSIS CERTIFICATE - CEMENT

TYPICAL RESULTS

Cement Type: CEM I 42,5 R (EN 197-1)

PERIOD: JUNE 2015

CE: 0099/CPR/A33/0154

N: 015/001358

The Quality Management System adopted in our company for the production and commercialization of cements and clinker, complies with UNE-EN-ISO 9001:2008, and it is certified by AENOR. It is also certified under IQNet network.

TESTS	Results	Specification EN 197-1
<b>Chemical Characteristics</b>		
Loss on Ignition %	2,50	≤ 5,0
SiO <sub>2</sub> %	19,87	
Al <sub>2</sub> O <sub>3</sub> %	5,27	
Fe <sub>2</sub> O <sub>3</sub> %	2,40	
CaO %	62,73	
MgO %	1,82	
Na <sub>2</sub> O %	0,21	
K <sub>2</sub> O %	1,13	
Insoluble Residue %	0,55	≤ 5,0
Sulphates (SO <sub>3</sub> ) %	3,29	≤ 4,0
Chlorides %	0,01	≤ 0,10
<b>Physical and Mechanical Characteristics</b>		
Normal Consistency Water %	29,5	
Initial Setting Time min	165	≥ 60
Final Setting Time min	225	
Soundness (Le Chatelier) mm	1,0	≤ 10
Specific Surface (Blaine) cm <sup>2</sup> /g	3730	
Compressive Strength at 2 days MPa	33,9	≥ 20,0
Compressive Strength at 28 days MPa	59,0	42,5-62,5
<b>Other Characteristics</b>		
Na <sub>2</sub> O equiv. %	0,96	
<b>Bogue Composition (mineral phases) *</b>		
C <sub>3</sub> S %	53,2	
C <sub>2</sub> S %	22,1	
C <sub>3</sub> A %	11,7	
C <sub>4</sub> AF %	7,2	

\* Corresponding to clinker composition

R-25-4-52/5-Z

Quality Manager

Barrio la Estación, s/n.  
39410 Mataporquera (Cantabria)  
Tel. 942 770 058  
Fax 942 770 243  
info@alfainforma.com



GRUPO CEMENTOS PORTLAND VALDERRIVAS